检 测 报 告

报告编号：	TRJP2026331475214Y
产品名称：	超强瓷砖胶
规格型号：	/
委托单位：	湖南安塔新材料有限公司
检测机构：	西安拓然检测技术有限公司
检测类别：	委托检验

拓然TURAN 西安拓然检测技术有限公司

地址：陕西省西安市高新区西部大道170号丰泽科技园1号楼1-103室
网址：http://tuornovnoneop.com/
邮箱：xatrjiance@163.com
电话：4008323600

报告编号：TRJP2026331475214Y

委托单位	湖南安塔新材料有限公司		
委托单位地址	湖南省长沙县黄花镇崩坎村先岭组66号		
生产单位	湖南安塔新材料有限公司		
生产地址	湖南省长沙县黄花镇崩坎村先岭组66号		
产品名称	超强瓷砖胶	规格型号	/
检测类别	委托检验	商　　标	/
样品数量	6Kg	样品状态	完好
收样日期	2026年08月20日	检测日期	2026年08月20日-2026年09月20日
检测环境	温度15-25℃，湿度50-60%RH		
检测依据	Q/AT 001-2026《超强瓷砖胶》 GB 33372-2020《胶粘剂挥发性有机化合物限量》		
检测项目	见下一页		
检测结论	所检项目均符合检测依据要求		
备　　注	本次检测仅对样品负责，不承担其他连带责任		

主检：		西安拓然检测技术有限公司 （盖章）
签名：何爽	日期：2026年09月20日	
审核：		
签名：王小玲	日期：2026年09月20日	
批准：		
签名：林利美	日期：2026年09月20日	

测试结果汇总

序号	检测项目	单位	标准要求	检测结果	判定	检验方法
1	外观	/	粉料均匀，无结块、无异物	粉料均匀，无结块、无异物	合格	JC/T 547-2017
2	拉伸粘结原强度	MPa	≥0.5	0.6	合格	JC/T 547-2017
3	晾置时间 20min 拉伸粘结强度	MPa	≥0.5	0.6	合格	JC/T 547-2017
4	浸水后拉伸粘结强度	MPa	≥0.5	0.58	合格	JC/T 547-2017
5	总挥发性有机化合物（VOC）	g/kg	≤10	4.2	合格	GB/T23986.2-2023
6	游离甲醛	mg/kg	≤50	未检出	合格	GB/T 23993-2009
7	苯	mg/kg	不得检出	未检出	合格	GB/T 23990-2009
8	甲苯 + 二甲苯总和	mg/kg	≤100	未检出	合格	GB/T 23990-2009

0

样品图片



声 明

Statements

1. 报告无“报告专用章”或检测单位公章无效。
The report lacks a "Special Report Seal" or the testing institution's official seal is invalid.

2. 报告随意涂改复印无效，如复印需经本中心同意并加盖公章。
The copy of the report is invalid. If the copy shall be approved by the center and stamped with official seal.

3. 检测结果仅对所受试样品有效。
The test results are valid only for the tested samples.

4. 对报告若有异议，应于收到报告之日起十五日内向检测单位提出，逾期不予受理。委托方需要书面申请上传之后10个工作日之后方可查询。
Any objections to the report shall be submitted to the testing institution within fifteen days from the date of receipt; overdue submissions will not be accepted. The client may only access the report after submitting a written request and waiting for 10 working days.

5. 对于送检样品，样品信息委托方声称，本公司不对其真实性负责。
For the samples submitted for inspection, the sample information client claims that the Company is not responsible for their authenticity.

6. 委托方收到报告之日起一个月内未取回样品，视作允许检测单位自行处理。
If the client fails to collect the samples within one month from the date of receiving the report, it shall be deemed that the testing institution is permitted to dispose of them at its discretion.

7. 本报告不适用于司法案件的辅助材料或佐证材料
This report is not used as auxiliary or supporting materials for judicial cases

8. 出于为客户保密的协定，需出具委托方许可方可查询报告详情。
For the purpose of customer confidentiality agreement, the report shall be detailed with the permission of the client.

9. 扫描报告首页二维码，即可查询报告真伪，如有疑问，请联系邮箱：xatrjiance@163.com
Scan the QR code on the first page of the report to verify its authenticity. If you have any questions, please contact us at xatrjiance@163.com

拓然TURAN